

## MEDIUM PIPE DN15 to DN150

### FEATURES

- Meets the requirements of AS 1074
- Conforms to the requirements of AS 2419 & AS 4118
- Available in full lengths (6.5m) and ½ lengths (3.25m)
- Plain ends (Roll grooved or threaded as required)
- Available painted with red oxide primer or hot dipped galvanised to AS/ NZS 4792

### TECHNICAL DATA

- Painted Code: PMPP-(size DN) full lengths  
PMPP-(size DN)-3250 ½ lengths
- HDG Code: PMGP-(size DN) full lengths  
PMGP-(size DN)-3250 ½ lengths
- Size Range: DN15 – 150
- Min. Yield Strength: 250 mPa
- Min. Tensile Strength: 320 mPa
- Min. Elongation:  $5.65\sqrt{S^0}$  22%

### DIMENSIONS

Size DN	Wall Thickness (mm)	Mass (Kg/M)	Lengths Per Sling
15	2.6	1.20	217
20	2.6	1.56	127
25	3.2	2.41	91
32	3.2	3.10	61
40	3.2	3.57	61
50	3.6	5.03	37
65*	3.6	6.43	37
80*	4.0	8.37	19
100*	4.5	12.20	10
150*	5.0	19.70	5

\*Pipe is stocked plain end and roll grooved end.

- Pipeline operating pressure must be governed by the rating of the pipe joining method.
- Mill certificates can be supplied if requested at the time of order.

